

Naples

Product Code	Construction	Material	Weight	Thickness	Max Width
TXNL	Woven	100% Polyester	195 sq.m2	0.23mm	Up to
TXNL-RY	Woven	100% Recyclable	6.88oz/sq m	(±0.05mm)	320cm
TXNL-AM	Woven	100% Anti-microbial			(±1cm)

Description

Very high color brilliance

Features

Crease free, Ship folded

Applications

Light Box | Stand Construction |

Ink Compatibility Cutter

Dye Sub Transfer | Dye Sub Direct |

Compatibility

Sublimation | Both



Shrink (l): 1.53%

Shrink (w): 0.40%

Stretch (l): 1.87%

Stretch (w): 1.47%

Stretch at Burst (l): 77.00%

Stretch at Burst (w): 70.00%

Burst Strength (l): 70lbs/in.

Burst Strength (w): 281lbs/in.

Tensile Strength (l): 11 lbs/in.

Tensile Strength (w): 9 lbs/in.

Burst Strength: 217 lbs

Yellowing: 0.87 dE

Max Roll Length: 100m

Available Recycled: Yes

Available Anti-microbial: Yes

NFPA-701 flame retardance certified.
Recommended transfer settings for sublimation are
374°F-410°F for 40-100 seconds at 40psi.